



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 013 603 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
28.06.2000 Bulletin 2000/26

(51) Int. Cl.⁷: **C01B 3/40**, B01J 23/00,
B01J 23/755

(21) Application number: 99123665.4

(22) Date of filing: 29.11.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 22.12.1998 US 113544 P

(71) Applicant: Haldor Topsoe A/S
DK-2800 Lyngby (DK)

(72) Inventors:
• Dohrup, Jesper
2100 Copenhagen (DK)
• Jacobsen, Claus J.H.
3630 Jaegerspris (DK)
• Olsen, Christian
2750 Ballerup (DK)

(54) **Process for catalytical steam reforming of a hydrocarbon feedstock**

(57) Process for catalytic steam reforming of a carbonaceous feedstock with improved resistance to sulphur poisoning and sintering characterized by contacting the feedstock with a nickel catalyst supported on magnesium aluminum spinel, $\text{MgO} \cdot x\text{Al}_2\text{O}_3$, wherein the spinel support has a specific surface area $A_{\text{sp}}[\text{m}^2/\text{g}]$ higher than $400 \cdot \exp(-T_c/400^\circ\text{C})$ obtained by calcination at a temperature $T_c[^\circ\text{C}]$.

EP 1 013 603 A1

Description

[0001] The present invention relates to steam reforming of hydrocarbons by contact with a supported nickel catalyst having improved activity and resistance to sulphur poisoning.

[0002] In particular, the invention is directed to an improved catalyst support material of high surface spinel, optionally promoted by Group III, IV or lanthanide metals. High surface spinel carrier materials provide a much improved sulphur resistance when employing hydrocarbon feedstock with high content of sulphur compounds due to a reduced degree of sulphur coverage on the carrier surface. Thereby, retaining sufficient catalytic activity with sulphur compounds containing feedstock.

[0003] The surface area of the carrier depends on the calcination temperature actually employed in the preparation of the carrier.

[0004] It has been found that spinel carrier material having a specific surface higher than or equal to a certain value after calcination at a predetermined calcination temperature possesses the above advantageous properties.

[0005] Accordingly, the invention provides a process for catalytic steam reforming of a carbonaceous feedstock with improved resistance to sulphur poisoning and sintering characterised by contacting the feedstock with a nickel catalyst supported on magnesium aluminum spinel, $\text{MgO} \cdot x\text{Al}_2\text{O}_3$, with a specific surface area, $A_{\text{sp}}[\text{m}^2/\text{g}]$, higher than expressed by the formula $A_{\text{sp}} = 400 \cdot \exp(-T_c/400^\circ\text{C})$ obtained by calcination at a temperature $T_c[^\circ\text{C}]$ where $T_c \geq 400^\circ\text{C}$.

[0006] As mentioned herein before, steam reforming activity of the spinel supported nickel catalyst is further improved when promoting the catalysts by inclusion of additional metals.

[0007] Preferred metals are Zr, Y, W, La, Ce or a mixture of lanthanides including La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu, commercially available as lanthanide concentrate. The above metal promoters are preferably included in the catalyst in a total amount of 0.01% to 10% by weight, most preferred in an amount of 0.5% to 5% by weight. The nickel content in the catalyst will be between 10% and 60% by weight, preferably between 15% and 40% by weight.

[0008] When operating the inventive process in industrial scale, it may be sufficient to arrange the above catalyst as top layer in a catalyst bed of a conventional nickel steam reforming catalyst.

[0009] The above and further aspects and features of the invention will become more apparent from the following description illustrating by example specific embodiments of the invention.

Example 1

Preparation of high Surface Area Spinel

[0010] Preferably, the first precipitation step is conducted under an atmosphere containing no water vapour to prevent hydrolysis of the aluminum alkoxide. In practise, the precipitation can be conducted under ambient conditions as long as excessive storage under these conditions is not required.

[0011] A solution was prepared by dissolution of 1 kg (4.05 mole) of aluminum tri-sec-butoxide, $\text{Al}(\text{C}_4\text{H}_9\text{O})_3$, with stirring in a tank equipped with a condenser containing 20 kg of 1-propanol. Another solution containing 0.520 kg (2.02 mole) of magnesium nitrate hexahydrate, $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, dissolved in 1 kg of water and 10 kg of 1-propanol was rapidly added to the solution of $\text{Al}(\text{C}_4\text{H}_9\text{O})_3$ with intense stirring and a white precipitate formed. After 30 min. the precipitate was isolated by filtration, washed with 10 kg water and dried at 110°C . Calcination at 550°C for 4 hours yielded 0.275 kg of a pure MgAl_2O_4 spinel with a lattice constant of 8.076 Å, a crystal size of 41 Å and a surface area of 192 m^2/g .

[0012] Generally, this method can be applied using any aluminum alkoxide $\text{Al}(\text{OR})_3$ precursor and any alcohol solvent (R=alkyl).

Example 2

Preparation of high Surface Area Spinel

[0013] Preferably, the first precipitation step is conducted under an atmosphere containing no water vapour to prevent hydrolysis of the aluminum and magnesium alkoxide. In practise, the precipitation can be conducted under ambient conditions as long as excessive storage under these conditions is not required.

[0014] A solution was prepared by dissolution of 1 kg (6.18 mole) of aluminum triethoxide and 0.352 kg (3.08 mole) of magnesium ethoxide with stirring in a tank equipped with a condenser containing 30 kg of 99% ethanol. 1.5 kg of water was added to the solution with intense stirring and immediately a white precipitate formed. After 30 min. the white filtrate was collected by filtration. Upon calcination at 550°C for 4 hours 0.423 kg of a pure MgAl_2O_4 spinel is obtained with a lattice constant of 8.081 Å, a crystal size of 45 Å and a surface area of 183 m^2/g .

[0015] Generally, this method can be applied using any alkoxides of magnesium and aluminum. The alcohol can be

recovered from the aqueous filtrate by distillation - the details being dependent on the alcohol and alcoxides used.

Example 3

5 Steam Reforming Activity

[0016] A series of nickel catalysts containing 10% to 60% by weight of nickel and containing varying contents of Zr, La, Ce, Y, or W (stabilizer), where prepared by sequential impregnations of a shaped high surface area magnesium aluminum spinel carrier by methods known in the art with nickel nitrate and ziconyl nitrate, $ZrO(NO_3)_2$, zirconium carbonate, $Zr(CO_3)_2$, basic zirconium carbonate, $Zr(CO_3)_x(OH)_{4-2x}$, $X < 2$, lanthanum nitrate, $La(NO_3)_3$, cerium nitrate, $Ce(NO_3)_3$, yttrium nitrate, $Y(NO_3)_3$, or ammonium decatungstate, $(NH_4)_6H_2W_{12}O_{40}$. Before the impregnation with the stabilizer, the nickel nitrate was decomposed. After drying the tablets were loaded in a reactor and activated during heating to a temperature between 500°C and 850°C in a hydrogenflow containing 1% steam at atmospheric pressure.

[0017] The steam reforming activity was determined under the following conditions:

Catalyst sieve fraction,	mm	0.3-0.5
Catalyst amount,	g	0.025
Temperature,	°C	400-750
Feed gas composition,	Nl/h	
NH ₄		4.0
H ₂ O		16.0
H ₂		1.6

[0018] The activities obtained at 500°C are shown in Table 1.

[0019] Steam reforming activity of stabilized and unstabilized catalysts, here shown with 25% by weight nickel, relative to low surface area spinel (less than 25 m²/g) supported nickel catalyst, R67GR obtained from Haldor Topsøe A/S, Nymøllevej 55, DK-2800 Lyngby, Denmark, at 500°C.

Table 1

Catalyst	Stabilizer content (weight%)	Relative Activity
R67GR	0	100
Catalyst 1	0	142
Catalyst 2	1.7%La	149
Catalyst 3	1.6%Y	162
Catalyst 4	0.95%Zr	156
Catalyst 5	4.4%W	87
Catalyst 6	3.1%Ce	151

[0020] It is apparent from Table 1 that stabilizers Zr, L, Ce, Y have only minor influence on the steam reforming activity compared to the pure nickel catalyst. W stabilizer decreases the steam reforming activity.

Example 4

Sulphur Poisoning Capacity

[0021] A series of nickel catalysts containing 10% to 60% by weight of nickel and containing varying contents of Zr,

La, Ce, Y, or W (stabilizer) where prepared by sequential impregnations of a shaped high surface area magnesium aluminum spinel carrier by methods known in the art with nickel nitrate and zirconyl nitrate, $\text{ZrO}(\text{NO}_3)_2$, zirconium carbonate, $\text{Zr}(\text{CO}_3)_2$, basic zirconium carbonate, $\text{Zr}(\text{CO}_3)_x(\text{OH})_{4-2x}$, $x < 2$, lanthanum nitrate, $\text{La}(\text{NO}_3)_3$, cerium nitrate, $\text{Ce}(\text{NO}_3)_3$, yttrium nitrate, $\text{Y}(\text{NO}_3)_3$, or ammonium decatungstate, $(\text{NH}_4)_6\text{H}_2\text{W}_{12}\text{O}_{40}$. Before the impregnation with the stabilizer, the nickel nitrate was decomposed. After drying the tablets were loaded in a reactor and activated during heating to a temperature between 500°C and 850°C in a hydrogen flow containing 1% steam at atmospheric pressure.

[0022] The capacity against sulphur poisoning was determined under conditions described by I. Alstrup et al. in Applied Catalysis, 1 (1981) 303-314 with dihydrogen sulphide content in the hydrogen flow between 10 ppm and 12 ppm. The sulphur poisoning capacities obtained at 550°C are shown in Table 2.

[0023] Capacity against sulphur poisoning of stabilized and unstabilized catalysts, here shown with 25% by weight nickel, relative to low surface area spinel (less than 25 m²/g) supported nickel catalyst, R67GR obtained from Haldor Topsøe A/S, Denmark, at 500°C.

Table 2

Catalyst	Stabilizer content (weight%)	Capacity against sulphur poisoning
R67GR	0	100
Catalyst 1	0	231
Catalyst 2	1.7%La	239
Catalyst 3	1.6%Y	254
Catalyst 4	0.95%Zr	231
Catalyst 5	4.4%W	219
Catalyst 6	3.1%Ce	296

[0024] It is apparent from Table 2 that catalyst based on high surface area spinel have increased capacity against sulphur poisoning compared to conventional spinel based catalyst, and only minor influence of the stabilizer on the capacity against sulphur poisoning.

Example 5

Sintering stability

[0025] A series of nickel catalysts containing 10% to 60% by weight of nickel and containing varying contents of Zr, La, Ce, Y, or W (stabilizer) where prepared by sequential impregnations of a shaped high surface area magnesium aluminum spinel carrier by methods known in the art with nickel nitrate and zirconyl nitrate, $\text{ZrO}(\text{NO}_3)_2$, zirconium carbonate, $\text{Zr}(\text{CO}_3)_2$, basic zirconium carbonate, $\text{Zr}(\text{CO}_3)_x(\text{OH})_{4-2x}$, $x < 2$, lanthanum nitrate, $\text{La}(\text{NO}_3)_3$, cerium nitrate, $\text{Ce}(\text{NO}_3)_3$, yttrium nitrate, $\text{Y}(\text{NO}_3)_3$, or ammonium decatungstate, $(\text{NH}_4)_6\text{N}_2\text{W}_{12}\text{O}_{40}$. Before the impregnation with the stabilizer, the nickel nitrate was decomposed. After drying the tablets were loaded in a reactor and activated during heating to a temperature between 500°C and 850°C in a hydrogen flow containing 1% steam at atmospheric pressure.

[0026] The sintering stability was determined by exposing the catalysts to a steam/hydrogen atmosphere at 30 bar, 500°C and a steam to hydrogen ratio of 10 to 1 on a molar basis for more than 500 hours, and, subsequently, analyse the catalysts for steam reforming activity and capacity against sulphur poisoning as described in Examples 3 and 4, respectively.

[0027] The steam reforming activities and capacities against sulphur poisoning obtained after sintering are shown in Table 3.

[0028] Steam reforming activity and capacity against sulphur poisoning after sintering of stabilized and unstabilized catalysts are shown tested at 500°C with 25% by weight nickel, compared with a low surface area spinel (less than 25 m²/g) supported nickel catalyst, R67GR obtained from Haldor Topsøe A/S, Denmark, at 500°C.

Table 3

Catalyst	Stabilizer content (weight%)	Relative activity	Capacity against sulphur poisoning
R67GR	0	100	100
Catalyst 1	0	100	192
Catalyst 2	1.7%La	132	242
Catalyst 3	1.6%Y	129	242
Catalyst 4	0.95%Zr	121	217
Catalyst 5	4.4%W	79	258
Catalyst 6	3.1%Ce	139	

Claims

1. Process for catalytic steam reforming of a carbonaceous feedstock with improved resistance to sulphur poisoning and sintering characterized by contacting the feedstock with a nickel catalyst supported on magnesium aluminum spinel, $MgO \cdot xAl_2O_3$, wherein the spinel support has a specific surface area $A_{sp}[m^2/g]$ higher than $400 \cdot \exp(-T_c/400^\circ C)$ obtained by calcination at a temperature $T_c[^\circ C]$.
2. The process of claim 1, wherein the molar ratio of magnesium to aluminum is between 1.5 and 3.0.
3. The process of claim 1, wherein the catalyst further contains at least one of the metals Zr, Y, W, La, Ce or lanthanide raw concentrate in a total amount of 0.01% to 10% by weight.
4. The process of claim 2, wherein the amount of the elements Zr, Y, W, La, Ce or lanthanide raw concentrate is between 0.5% and 5% by weight.
5. The process of claim 1, wherein the amount of nickel is between 10% and 60% by weight.
6. The process of claim 1, wherein the amount of nickel is between 15% and 40% by weight.
7. The process of claim 1, wherein magnesium aluminum spinel supported nickel catalyst is arranged as a toplayer in a fixed bed of a conventional nickel steam reforming catalyst.
8. The process of claim 7, wherein the toplayer constitutes between 5% and 50% of the total catalyst bed.
9. The process according to anyone of the preceding claims, wherein the calcination temperature is higher than $400^\circ C$.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 3665

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	J. XU, G. F. FROMENT: "Methane steam reforming, methanation and water-gas shift: 1. Intrinsic kinetics" AICHE JOURNAL, vol. 35, no. 1, January 1989 (1989-01), pages 88-96, XP000892972 * page 88 *	1	C01B3/40 B01J23/00 B01J23/755
A	EP 0 470 626 A (TOPSOE HALDOR AS) 12 February 1992 (1992-02-12) * examples 2,10 *	1	
A	DATABASE WPI Section Ch, Week 199703 Derwent Publications Ltd., London, GB; Class E36, AN 1997-032324 XP002133943 & RU 2 054 963 C (EMEKAT RES PRODN ASSOC), 27 February 1996 (1996-02-27) * abstract *	1-6	
A	US 3 436 358 A (THYGESEN POUL) 1 April 1969 (1969-04-01) * the whole document *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C01B B01J C01F
A	EP 0 640 560 A (TOPSOE HALDOR AS) 1 March 1995 (1995-03-01) * examples 1,2 *	1,7,8	
A	US 4 542 112 A (MATSUI MINORU ET AL) 17 September 1985 (1985-09-17) * example 1 *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 28 March 2000	Examiner Van der Poel, W
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document	

EPO FORM 1803 03.92 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 12 3665

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-03-2000

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0470626	A	12-02-1992	DK 189890 A	10-02-1992
			AU 629131 B	24-09-1992
			AU 8167591 A	13-02-1992
			DE 69109203 D	01-06-1995
			DE 69109203 T	31-08-1995
			JP 4227062 A	17-08-1992
			US 5599517 A	04-02-1997
			US 5595719 A	21-01-1997
RU 2054963	C	27-02-1996	NONE	
US 3436358	A	01-04-1969	DK 118184 B	20-07-1970
			BE 641944 A	16-04-1964
			DE 1542505 A	16-04-1970
			FI 42352 B	31-03-1970
			NL 140815 B	15-01-1974
			NO 117931 B	13-10-1969
EP 0640560	A	01-03-1995	DK 97493 A	28-02-1995
			AU 673451 B	07-11-1996
			AU 7147394 A	09-03-1995
			CA 2130953 A	28-02-1995
			DE 69407692 D	12-02-1998
			DE 69407692 T	16-04-1998
			ES 2111811 T	16-03-1998
			JP 2958242 B	06-10-1999
			JP 7144902 A	06-06-1995
			KR 124987 B	27-11-1997
			NO 943145 A	28-02-1995
			NZ 264308 A	26-03-1996
			US 5498404 A	12-03-1996
			ZA 9406517 A	28-03-1995
US 4542112	A	17-09-1985	JP 1031460 B	26-06-1989
			JP 1546770 C	28-02-1990
			JP 59073431 A	25-04-1984
			EP 0110490 A	13-06-1984

EPC FORM P0689

For more details about this annex: see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)